



shown on front: LCL40 8x36 Market & LCL145/M12CUBE Cool Mix Cube

The poet, Rumi, wrote "... there are a thousand ways to go home again."

The seasoned color palette of Bistro, Café, Lounge, Market, and Tavern will give any interior or exterior space tone and personality. The refined white, cool and warm grays, calming creams, and

Local has created five of the most unique ways home. This glazed taupes set a mood that is welcoming and chic, delivering you porcelain floor and wall tile allows you to your favorite local haunt. An 8x36 pressed plank provides a to design an atmosphere that creates a sense of connection format that works well in an array of traditional, contemporary, – a place of both possibility and comfort – a place to linger or eclectic environments. A 2x12 herringbone mosaic available and belong. The look of weathered, painted wood introduces in each of the five colors, as well as warm and cool mix cube comfort and familiarity that is rustic...yet graceful. It transcends mosaics make a modern and impactful statement. locale and invites you to be part of the community and its story.

below: LCL10 8x36 Bistro & LCL10/M2x12HER Bistro



## BISTRO



LCL10 8x36 Bistro



**LCL10/M2x12HER**Bistro



**LCL123/M12CUBE** Warm Mix Cube (Café, Bistro, and Tavern)



**LCL145/M12CUBE**Cool Mix Cube
(Lounge, Bistro, and Market)

## TAVERN



**LCL20 8x36** Tavern



LCL20/M2x12HER Tavern



LCL123/M12CUBE Warm Mix Cube (Café, Bistro, and Tavern)

# CAFÉ



**LCL30 8x36** Café



LCL30/M2x12HER Café




**LCL123/M12CUBE**Warm Mix Cube
(Café, Bistro, and Tavern)

### MARKET



LCL40 8x36 Market



LCL40/M2x12HER Market




LCL145/M12CUBE Cool Mix Cube (Lounge, Bistro, and Market)

# LOUNGE



LCL50 8x36 Lounge



LCL50/M2x12HER Lounge



**LCL145/M12CUBE**Cool Mix Cube
(Lounge, Bistro, and Market)



above: LCL30 8x36 Café

Porcelain Technical Data Properties (Floor)	ASTM®	ANSI®	Results <sup>1</sup>	
DCOF AcuTest <sup>®2</sup>	A137.1	≥ 0.42	Pass	
Surface Hardness	Mohs Scale	N/A	7 Mohs	
Break Strength	C-648	≥ 250 lbf.	≥ 474 lbf. avg.	
Water Absorption	C-373	≤ 0.5%	≤ 0.5%³	
Intended Use <sup>4</sup>	N/A	N/A	Residential Light Commercial Heavy Commercial	

<sup>&</sup>lt;sup>1</sup> Values are offered in good faith as being accurate and typical of normal production. Due to the natural variation of raw materials and manufacturing processes, the values of the purchased product for any particular installation may vary.

### **Typical Uses**

Local<sup>DP</sup> glazed porcelain floor and wall tile is appropriate for residential and commercial wall, countertop, backsplash, and most floor applications.

Notice: Not all flooring products are suitable for wet areas, specialized applications, or commercial use. Please refer to the American National Standard Specifications for Ceramic Tile (ANSI® A137.1) for ceramic, stone, and glass installation for specific usage and installation information.

This product will contribute to USGBC LEED® points and the ANSI® approved NAHB® Green Building Points.

Color, texture, and finish variations may occur due to the nature of the product.

Color reproductions in this printed piece may vary from actual tile colors. Final selection should be made from actual tile samples.

Field Tile Nominal Size (in) <sup>1</sup>	Metric (cm)	Pcs./Sq Ft <sup>2</sup>	Thickness <sup>3</sup>	Edge
8x36	20x90	.5	9mm <sup>4</sup>	Pressed

<sup>&</sup>lt;sup>1</sup>These values may vary from lot to lot.

#### **Herringbone Mosaic Notice:**

Each M2x12HER Herringbone Mosaic is two parts, side A and side B; This item is sold (6) pieces per carton, in sets of (3) A's and (3) B's; The total coverage per carton is 5.7 SQFT.

# **Color Variation**

#### **V3 Moderate Variation**

While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece may vary significantly. For example "that little bit of color" on one piece of tile may be the primary color on the next piece.



















<sup>&</sup>lt;sup>2</sup> ANSI® A137.1 standard, ceramic tiles selected for level interior spaces expected to be walked upon when wet must have a minimum wet DCOF AcuTest® value of 0.42.

<sup>&</sup>lt;sup>3</sup> Average production value.

<sup>&</sup>lt;sup>2</sup>These values are based on actual sizes including the grout joint.

<sup>&</sup>lt;sup>3</sup> May not apply to textured surfaces or tiles with uneven back patterns such as mesh

<sup>&</sup>lt;sup>4</sup> In order to enhance manufacturing efficiencies this product has been modified to a 9mm thickness. During implementation of this modification, some 10mm products will remain available. Please confirm the thickness of your product at time of order.